

## ELIX™ 190 TE

Acrylonitrile Butadiene Styrene / PTFE system.

---

### ***Typical applications***

. Used as anti-dripping additive in Flame Retardant formulations of ABS, PC+ABS and High Impact Polystyrene (HIPS).

### ***Chemical composition***

Acrylonitrile-Butadiene-Styrene Copolymer with encapsulated PTFE.

### ***Physical form***

White to slightly yellow powder.

### ***Handling information***

Please see the Material Safety Data Sheet for relevant health & safety information.

### ***Typical properties***

Polybutadiene content : 50-53%	<b><i>ELIX Polymers Lab (internal) – IR</i></b>
PTFE content : 9,5-11%	<b><i>ELIX Polymers Lab (internal) – IR</i></b>
Residual monomers : max. 800 ppm	<b><i>ELIX Polymers Lab (internal) – GC</i></b>
Moisture content : max. 1,0%	<b><i>ELIX Polymers Lab (internal)</i></b>
Bulk density at 23°C : 250-350 g/L	<b><i>ELIX Polymers Lab (internal)</i></b>

Note : control measurements in other places may issue different results due to influences of machinery, equipment, test method or storage conditions.

### ***Disclaimer for sales products***

#### Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided –especially that contained in our safety data and technical information sheets– and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

#### Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

**ELIX Polymers, S.L. - E-43006 Tarragona**

© INEOS ABS. All rights reserved.

---

Edition 01/10

[infomsds@lustran-polymers.com](mailto:infomsds@lustran-polymers.com)