

Need more information? [Click Here](#) to go to the UL iQ™ for Plastics database

Component - Plastics

E350602

ELIX POLYMERS SL

POLIGONO INDUSTRIAL, APARTADO DE CORREOS 176, CTRA DE VILA-SECA A LA PINEDA,
TARRAGONA 43080 ES

4000PG

Acrylonitrile Butadiene Styrene (ABS), "ELIX ULTRA", furnished as pellets

Color	Min Thk (mm)	Flame Class	Flame		RTI Elec	RTI Imp	RTI Str
			HWI	HAI			
NC	1.5	HB	-	-	60	60	60
	3.0	HB	-	-	60	60	60

Comparative Tracking Index (CTI): -

Inclined Plane Tracking (IPT): -

Dielectric Strength (kV/mm): -

Volume Resistivity (10^x ohm-cm) : -

High-Voltage Arc Tracking Rate
(HVTR): -

High Volt, Low Current Arc Resis (D495): -

Dimensional Stability (%): -

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2005-01-11

Last Revised: 2011-10-20

© 2011 Underwriters Laboratories Inc.



IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness		Value
			Tested (mm)		
Flammability	IEC 60695-11-10	Class (color)	1.5		HB75 (NC)
			3.0		HB40 (NC)
Glow-Wire Flammability (GWI)	IEC 60695-2-12	C	-		-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-		-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-		-
IEC Ball Pressure	IEC 60695-10-2	C	-		-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-		-
ISO Tensile Strength	ISO 527-2	MPa	-		-
ISO Flexural Strength	ISO 178	MPa	-		-
ISO Tensile Impact	ISO 8256	kJ/m ²	-		-
ISO Izod Impact	ISO 180	kJ/m ²	-		-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-		-

© 2011 Underwriters Laboratories Inc.

The materials covered in this database are incomplete in certain constructional features or restricted in performance capabilities and are intended for use as components of complete equipment submitted for investigation rather than for direct separate installation in the field. THE FINAL ACCEPTANCE OF THE COMPONENT IS DEPENDENT UPON ITS INSTALLATION AND USE IN COMPLETE PRODUCTS SUBMITTED TO UNDERWRITERS LABORATORIES.

Notice of Disclaimer