

## ELIX ABS H604

Improved heat, chemical and dynamical resistance

### Typical properties\*

| Property                                            | Test Condition | Standard       | Unit         | Value   |
|-----------------------------------------------------|----------------|----------------|--------------|---------|
|                                                     |                |                | SI Metrics   |         |
| Rheological properties                              |                |                |              |         |
| Melt volume-flow rate                               | 220 °C; 10 kg  | ISO 1133       | cm³/(10 min) | 12      |
| Molding shrinkage, normal                           | 60x60x2 mm     | ISO 294-4      | %            | 0.5-0.7 |
| Molding shrinkage, parallel                         | 60x60x2 mm     | ISO 294-4      | %            | 0.5-0.7 |
| Mechanical properties (23 °C/50 % r. h.)            |                |                |              |         |
| Yield stress                                        | 50 mm/min      | ISO 527-1,-2   | MPa          | 45      |
| Tensile modulus                                     | 1 mm/min       | ISO 527-1,-2   | MPa          | 2400    |
| Yield strain                                        | 50 mm/min      | ISO 527-1,-2   | %            | 2,4     |
| Flexural strength                                   | 2 mm/min       | ISO 178        | MPa          | 73      |
| Flexural modulus                                    | 2 mm/min       | ISO 178        | MPa          | 2500    |
| Izod notched impact strength                        | 23 °C          | ISO 180-1A     | kJ/m²        | 21      |
|                                                     | -30 °C         | ISO 180-1A     | kJ/m²        | 12      |
| Charpy unnotched impact strength                    | 23 °C          | ISO 179-1eU    | kJ/m²        | 140     |
|                                                     | -30 °C         | ISO 179-1eU    | kJ/m²        | 85      |
| Charpy notched impact strength                      | 23 °C          | ISO 179-1eA    | kJ/m²        | 20      |
|                                                     | -30 °C         | ISO 179-1eA    | kJ/m²        | 9       |
| Ball indentation hardness                           |                | ISO 2039-1     | N/mm²        | 102     |
| Thermal properties                                  |                |                |              |         |
| Temperature of deflection under load                | 0.45 MPa       | ISO 75-1,-2    | °C           | 102     |
|                                                     | 1.80 MPa       | ISO 75-1,-2    | °C           | 98      |
| Vicat softening temperature                         | 50 N; 50 °C/h  | ISO 306        | °C           | 100     |
|                                                     | 50 N; 120 °C/h | ISO 306        | °C           | 104     |
| Burning behavior UL 94 (1.6 mm)                     | 1.6 mm         | UL 94          | Class        | HB      |
| Coefficient of linear thermal expansion, parallel   | 23 to 55 °C    | ISO 11359-1,-2 | 10-4/K       | 0,8     |
| Coefficient of linear thermal expansion, transverse | 23 to 55 °C    | ISO 11359-1,-2 | 10-4/K       | 0,8     |
| Burning rate (US-FMVSS)                             | 2.0 mm         | ISO 3795       | mm/min       | <80     |
| Glow wire test (GWFI)                               | 2.0 mm         | IEC 60695-2-12 | °C           | 675     |
| Electrical properties (23 °C/50 % r. h.)            |                |                |              |         |
| Relative permittivity                               | 100 Hz         | IEC 60250      | -            | 3       |
|                                                     | 1 MHz          | IEC 60250      | -            | 2,9     |
| Dissipation factor                                  | 100 Hz         | IEC 60250      | 10-4         | 50      |
|                                                     | 1 MHz          | IEC 60250      | 10-4         | 90      |
| Volume resistivity                                  |                | IEC 60093      | Ohm·m        | 1E14    |

| Property                                        | Test Condition | Standard    | Unit              | Value |
|-------------------------------------------------|----------------|-------------|-------------------|-------|
| Surface resistivity                             |                | IEC 60093   | Ohm               | 1E16  |
| Electric strength                               | 1 mm           | IEC 60243-1 | kV/mm             | 31    |
| Comparative tracking index CTI                  | Solution A     | IEC 60112   | Rating            | 600   |
| <b>Other properties (23 °C)</b>                 |                |             |                   |       |
| Density                                         |                | ISO 1183    | g/cm <sup>3</sup> | 1,04  |
| <b>Processing conditions for test specimens</b> |                |             |                   |       |
| Injection molding-Melt temperature              |                | ISO 294     | °C                | 240   |
| Injection molding-Mold temperature              |                | ISO 294     | °C                | 70    |
| Injection molding-Injection velocity            |                | ISO 294     | mm/s              | 240   |

\*Control measurements in other places may issue different results due to influences of machinery, equipment, test method or storage conditions.

### **Disclaimer for sales products**

#### Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided –especially that contained in our safety data and technical information sheets– and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery

#### Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

#### Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

### **ELIX Polymers, S.L. - E-43006 Tarragona**

Edition Version: 6 - 22.01.2025

[info@elix-polymers.com](mailto:info@elix-polymers.com)