



Component - Plastics

File Number: E350602

ELIX POLYMERS SL
POLIGONO INDUSTRIAL
CTRA DE VILA-SECA A LA PINEDA
LA CANONJA, 43110 Spain



ELIX ABS: P3H-AT, P3H-CC
Acrylonitrile Butadiene Styrene (ABS), pellets

Flammability	Value	Test Method
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
1.5 mm	PLC 4	
3.0 mm	PLC 3	
High Amp Arc Ignition (HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746
Dielectric Strength	22 kV/mm	ASTM D149 IEC 60243-1
High Voltage Arc Tracking Rate (HVTR)	PLC 1	UL 746
Volume Resistivity	1.0E+16 ohms-cm	ASTM D257 IEC 60093
Arc Resistance	PLC 5	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
1.0 mm	85.0 °C	
1.5 mm	85.0 °C	
3.0 mm	85.0 °C	
RTI Imp		UL 746
1.5 mm	80.0 °C	
3.0 mm	80.0 °C	
RTI Str		UL 746
1.5 mm	85.0 °C	
3.0 mm	85.0 °C	
Physical	Value	Test Method
Dimensional Stability	0.0 %	ASTM D1042 ISO 2796