
ELIX ABS 118HF

Very high flow ABS, high gloss surface with antistatic additive

Product properties

Very high flow ABS material.
Excellent balance of impact strength and flowability.
High gloss surface finish.
Used as base resin for improved flowability
Housing big parts.
Thin-walled parts.

Chemical composition

Acrylonitrile-Butadiene-Styrene Copolymer.

Physical form

Pellets

Handling information

Please see the Material Safety Data Sheet for relevant health & safety information.



Typical properties

Property	Test Condition	Unit	Standard	Value
Rheological properties				
Melt volume-flow rate	220°C, 10Kg	cm ³ /10 min	ISO 1133	57
Molding shrinkage, parallel	60x60x2 mm	%	ISO 294-4	0.5-0.7
Molding shrinkage, normal	60x60x2 mm	%	ISO 294-4	0.5-0.7
Mechanical properties (23°C /50% H.R.)				
Yield stress	50 mm/min	MPa	ISO 527-1,2	42
Elongation at break	50 mm/min	%	ISO 527-1,2	34
Tensile modulus	1 mm/min	MPa	ISO 527-1,2	2260
Flexural modulus	2 mm/min	MPa	ISO 178	2350
Flexural strength	2 mm/min	MPa	ISO 178	66
Izod notched impact strength	23 °C	KJ/m ²	ISO 180-1A	14
Izod notched impact strength	-30 °C	KJ/m ²	ISO 180-1A	7
Ball indentation hardness		N/mm ²	ISO 2039-1	92
Thermal properties				
Vicat softening temperature	B50, 50°C/h	°C	ISO 306	98
Deflection temperature under load	1.80 MPa	°C	ISO 75-1,2	94
Deflection temperature under load	0.45	°C	ISO 75-1,2	98
CLTE, parallel	23 to 55 °C	10 ⁻⁴ /K	ISO 11359-1,2	0.9
Burning behavior UL 94	1.6 mm	Class	UL 94	HB
Burning rate (US-FMVSS)	200x105x2mm	mm/min	ISO 3795	< 60
Other properties (23°C)				
Density	25°C	Kg/m ³	ISO 1183-1	1.03
Processing conditions for test specimens				
Injection molding-melt temperature	240	°C	ISO 294	
Injection molding-mold temperature	70	°C	ISO 294	
Injection molding-injection velocity	240	mm/s	ISO 294	

Note : control measurements in other places may issue different results due to influences of machinery, equipment, test method or storage conditions.

Disclaimer for sales products

Disclaimer for sales products

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided –especially that contained in our safety data and technical information sheets– and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold and our advisory service is given in accordance with the current version of our General Conditions of Sale and Delivery.

Test values

Unless specified to the contrary, the values given have been established on standardised test specimens at room temperature. The figures should be regarded as guide values only and not as binding minimum values. Kindly note that, under certain conditions, the properties can be affected to a considerable extent by the design of the mould/die, the processing conditions and the colouring.

Processing note

Under the recommended processing conditions small quantities of decomposition product may be given off during processing. To preclude any risk to the health and well-being of the machine operatives, tolerance limits for the work environment must be ensured by the provision of efficient exhaust ventilation and fresh air at the workplace in accordance with the Safety Data Sheet. In order to prevent the partial decomposition of the polymer and the generation of volatile decomposition products, the prescribed processing temperatures should not be substantially exceeded. Since excessively high temperatures are generally the result of operator error or defects in the heating system, special care and controls are essential in these areas.

ELIX Polymers, S.L. - E-43006 Tarragona

Edition 03.07.2019

info@elix-polymers.com